

PARAFFIN MANUFACTURING CO.

HEAVY SLACK WAX

CHARACTERISTIC	RESULT	MLETHOD
Oil content	12% wt	ASTM D-938
Melting Point	54-62 °C	ASTM D-938
Flash Point	Min.245 °C	ASTM D-92
Density at °C	0.885 kg/l	ASTM D-4052
Colour (Lovibond)	Brown	Method (2"cell

Packing:
Drum/ Metalized Bag