

PARAFFIN MANUFACTURING CO.

HEAVY SLACK WAX

PRODUCT DATA SHEET

CHARACTERISTIC	RESULT	MLETHOD
Oil content	Max 35 wt%	ASTM D-721
Drop Melting Point	65 °C	ASTM D-127
Congealing Point	61 °C	ASTM D-937
Flash Point	265 °C	ASTM D-92
Kinematic viscosity@100°C	8 CST	ASTM: D-445
Specific Gravity 25 °C / 25 °C	0.855	ASTM: D-190
Colour	2.0 (Brown)	ASTM: D-1500

Packing:
Drum/ Metalized Bag